

Probenbe	Click Vinyl Plank/Tile, 106100132(66314)
Aktenzeic	II 44 1.156.603-193/10
Prü	ALAB GmbH

Ergebnisü ADAM_2010_05	3 Tage (days)			7 Tage (days)			28 Tage (days)		
	Ergebnisse results	AgBB Anforderungen	Abbruchkriterien break-off criteria	Ergebnisse results	Abbruchkriterien break-off criteria	Ergebnisse results	AgBB Anforderungen	Abbruchkriterien break-off criteria	
	µg/m³	mg/m³	mg/m³	µg/m³	mg/m³	µg/m³	mg/m³	mg/m³	
[A] TVOC (C ₆)	362	0 ≤ 10 mg/m³	0.4 !! ≤ 0,3 mg/m³	177	0.2 ≤ 0,5 mg/m³	99	0.1 ≤ 1,0 mg/m³		
[B] Σ SVOC (C ₆)	0		0.00 ≤ 0,03 mg/m³	0	0.00 ≤ 0,05 mg/m³	0	0.0 ≤ 0,1 mg/m³		
[C] R (dimensionsl)	0.120		0.1 ≤ 0,5	0.063	0.1 ≤ 0,5	0.027	0 ≤ 1		
[D] Σ VOC o. NIK without LCI	0		0.00 ≤ 0,05 mg/m³	0	0.00 ≤ 0,05 mg/m³	0	0.0 ≤ 0,1 mg/m³		
[E] Σ Cancer	5	0.01 ≤ 0,01 mg/m³	0.005 !! ≤ 0,001 mg/m³	2	0.002 !! ≤ 0,001 mg/m³	1	0.001 ≤ 0,001 mg/m³		

Dieser Block liefert zusätzliche Information
 This part gives some additional information

[F] VVOC (< C ₆)	180			63			36	
[G] als Toluolä quivalent as toluene equivalent		Wert manuell eingeben! Enter value manually!			Wert manuell eingeben! Enter value manually!			Wert manuell eingeben! Enter value manually!